



3320 Lowson Blvd. Delray Beach Florida 33445, USA (561) 350-6923

www.GlobalPetroMetal.com

Used Rails

Chemical Composition

This document is not intended to replace the Chemical Composition Analysis our customers will receive from the Société Générale de Surveillance (SGS).

C: 0,54-0,82

Si.: 0,18-0,40

Mn: 0,60-1,05

S: 0.04 max

P.: 0,035 max

As.: 0.01 max of Mass share

Norms: **R-50** GOST-7173-75 and **R-65** GOST-8165-75

The scrap consists of R-50 (51,67 kg/m) R-65 (64,72 kg/m) Used Rail ISRI 27-29